


# *Development and Characterization of Materials and Coatings for e-cloud mitigation @ LNF.*

*Roberto Cimino LNF-INFN*

*For the NTA-IMCA and Nuvola-GrV collaboration*


- Introduction to the e-cloud problem*
- Ongoing work in other Laboratories (state of the art)*
- Material Science Laboratory@LNF first results.*
- Conclusion.*

# The "e-cloud" phenomenon (in pils)



The accelerated particle beam produces SR and/or  $e^-$  that, by hitting the accelerator's walls generate photo- $e^-$  or secondary- $e^-$ . Such  $e^-$  can interact with the beam (most efficiently for positive beams) and multiply, inducing additional heat load on the walls, gas desorption and may cause severe detrimental effects on machine performance.


# One of the most relevant parameter for e-cloud studies is: $S.E.Y.$ (or $\delta$ )



*I.e.: the number of electrons created after bombardment of a single electron.*


*R. Cimino, et al.,  
Phys. Rev. Lett.  
93 (2004) 014801*

SECONDARY ELECTRON YIELD  
As received




*Measure of  
Secondary  $e^-$   
YIELD*

arc heat load vs. intensity, 25 ns spacing, 'best' model



heat load for quadrupoles higher  
in 2<sup>nd</sup> batch; still to be clarified

*.... And its impact to  
simulations (see calculation  
for LHC).*




*See: CERN-GSI Electron Cloud  
Workshop. CERN 7-3-2011*

# *e-cloud @ LHC: a Real Issue*


# First observation of e-cloud activity @ LHC: 8-10-2010.

## 150 ns bunch spacing: Merged vacuum


6



# *Easily solved: Installation of Solenoids*




# Solenoids effect on pressure





## → OBSERVATIONS IN 2010 @ LHC:



Pressure rises with 75ns bunch spacing were observed in IR3  
Even though  $P \sim 10^{-6}$  mbar, 936 bunches could be filled in

→ **PLAN FOR 2011:** Scrubbing using 50ns bunch trains

Physics operation using 75ns

→ **GOAL:** Investigate SEY parameters such that e-clouds do not limit physics operation

# 3. Plans for Super KEKB

Y. Suetsugu, KEK  
on behalf of KEKB Vacuum Group

- Required electron density to avoid single bunch instability

K. Ohmi, KEK Preprint 2005-100 (2006)

$$\rho_{e,th} = \frac{2\gamma\nu_s\omega_{e,y}\sigma_z/c}{\sqrt{3}KQr_e\beta L}$$

Here,

$$\omega_{e,y} = \sqrt{\frac{\lambda_+ r_e c^2}{\sigma_y(\sigma_x + \sigma_y)}}$$

$E$ [GeV]	= 4.0	$N_b$	= 6.25E+10	
$\gamma$	= 7828	$Q_b$ [C]	= 1.4E-08	(1.4 mA/bunch)
$\nu_s$	= 0.0185	$S_b$ [m]	= 1.2	(4ns)
$\sigma_z$ [m]	= 6.E-03	$\lambda$ [C/m]	= 5.2E+12	( $Q_b/2/\sigma_z$ )
$c$ [m/s]	= 3.E+08	$\sigma_y$ [m]	= 2.E-05	
$K$	= 11	$\sigma_x$ [m]	= 2.E-04	
$Q$	= 7			
$r_e$ [m]	= 2.80E-15	$\omega_e$	= 5.46E+11	$K = \omega_e \sigma_z/c$
$\beta_y$ [m]	= 25	$\omega_e \sigma_z/c$	= 10.9	$Q = \text{Min}(Q_{nl}, \omega_e \sigma_z/c)$
$L$ [m]	= 3016			$Q_{nl} \sim 7$

$$\rho \text{ [m}^{-3}\text{]} = 1.13\text{E}11$$



$$\text{Our target} = 1\text{E}11 \text{ m}^{-3}$$

# Single Bunch Instability Threshold for Super-B (courtesy of T. Demma)

		June 2008		January 2009		March 2009		Sep.2009
		$\rho_{\text{int}} [10^{15}\text{m}^{-2}]$ solenoids	$\rho_{\text{int}} [10^{15}\text{m}^{-2}]$ no solenoids	$\rho_{\text{int}} [10^{15}\text{m}^{-2}]$ solenoids	$\rho_{\text{int}} [10^{15}\text{m}^{-2}]$ no solenoids	$\rho_{\text{int}} [10^{15}\text{m}^{-2}]$ solenoids	$\rho_{\text{int}} [10^{15}\text{m}^{-2}]$ no solenoids	$\rho_{\text{center}}$
SEY=1.1	95%	0.06	2.1	0.09	2.5	0.22	2.7	0.1
	99%	0.02	0.25	0.04	0.3	0.04	0.7	0.07
SEY=1.2	95%	0.22	2.8	0.27	3.2	0.45	6.5	0.3
	99%	0.045	0.71	0.06	0.82	0.07	2.4	0.1
SEY=1.3	95%	2.7	20.2	2.9	25.7	5.4	25	2.0
	99%	0.94	3.2	1.3	4.1	4.5	13	0.7

*Most of the existing and planned accelerator machines base the reaching of their design parameters to the capability of obtaining walls with a SEY  $\sim 1.2$  or below!  
(This includes the Damping Rings of interest to this workshop!)*

*Surface Scrubbing  
(or conditioning)*

*Intrinsically low  
SEY material*

*Geometrical  
modifications*

*Electrodes in the lattice.*

*External solenoid field*

*Surface Scrubbing  
(or conditioning)*



*-Efficiency  
(time & final SEY)...*

*Geometrical  
modifications*



*Impedance.  
Machining costs.*

*Intrinsically low  
SEY material*



*Stability and material  
choice...*

*Electrodes in the lattice.*



*If possible...  
(Impedance, costs.)*

*External solenoid field.*



*Not always possible...*

# *Activity of the LNF Material Science Laboratory:*

*Our Laboratory is becoming a reference Lab for material science analysis and tests of relevance for e-cloud studies.*

*We are studying (in collaboration with the respective institutes):*



- *CERN- LHC (Dipole chamber) Cu Samples*
- *CERN – SPS a-C Coatings*
- *Al from DAFNE and PETRA 3 (DESY)*
- *Stainless Steel (from RICH, Brookhaven)*
- *TiN “test” samples produced at LNF and from PEP*
- *NEGs .....*

*... and we are learning a lot!!!*

- Together with the SEY experiments, @ LNF, we are able to “see” the chemical modification at the surface. This will be more effective by using two SR beamlines from a DAFNE BM which we are now carefully aligning and commissioning!




# LNF XUV Beam Lines



XUV-H (60-10000)

When ready we will be one of the few laboratory in the world to be able to analyse SEY (PEY) variation after electron and photon scrubbing on the same samples. This is a situation which does occur in real accelerators, but it has never been studied in a laboratory experiment.



XUV-L (35-200) eV

V. TULLIO 2009



*We are working on up a State of the art Surface Science system to study, produce and test low SEY films.*

*Manipulator*

*Sample Prep. Chamber for reactions*

*Farady Cup*

*HEB SR Beamline (60-1000 eV)*


*Electron Analyser*

*LEED + e<sup>-</sup> gun*


*e<sup>-</sup> gun*

*X-ray Lamp*

LCWS11 29-9-2011




*Our study on the Cu surfaces of the LT dipole regions of LHC: “scrubbing” and chemical modifications*




The Beam “scrubbing” effect is the ability of a surface to reduce its SEY after  $e^-$  bombardment.

from LHC PR 472 (Aug. 2001): “...Although the phenomenon of conditioning has been obtained reproducibly on many samples, the exact mechanism leading to this effect is not properly understood. This is of course not a comfortable situation as the LHC operation at nominal intensities relies on this effect...”



V. Baglin et al, LHC Project Report 472, CERN, 2001.


# Photoemission spectroscopy during electron scrubbing.



\*Cimino et al. not published

## Photoemission spectroscopy during electron scrubbing.



From photoemission spectra we notice that on LHC copper samples, oxygen does not vary significantly with electron bombardment, and carbon levels shows a clear formation of a  $sp^2$  layer indicating a graphitization of the sample.



\*Cimino et al. not published


### Separation of the $sp^3$ and $sp^2$ components in the C 1s photoemission spectra of amorphous carbon films

Javier Díaz,\* Guido Paolicelli,† Salvador Ferrer, and Fabio Comin  
 European Synchrotron Radiation Facility, Boîte Postal 220, 38043 Grenoble Cedex, France  
 (Received 2 June 1995; revised manuscript received 18 December 1995)



*SEY and XPS studies: Al from DAFNE and  
Petra III (difficulties in reaching low  
emittance)*

# SEY and XPS studies: Al from DAΦNE and Petra III (difficulties in reaching low emittance)




*When you deal with industrially prepared materials: Not all the materials are what they are called!*

*D. R. Grosso et al in preparation*



# SEY and XPS studies: Al from Petra III (difficulties in reaching low emittance)




Three SEY spectra recorded in different conditions on Al technical samples cut from the inner walls of the Petra III storage ring,

(a) “as received”

(b) after electron scrubbing at 500 eV KE in UHV at background pressures of low  $10^{-9}$

(c) after electron scrubbing at 500 eV KE in UHV at background pressures of low  $10^{-10}$  mbar

# XPS studies on Al as received, sputtered clean and e<sup>-</sup> scrubbed in 10<sup>-8</sup> - 10<sup>-9</sup> mbar:



The XPS characterization of the sample surface, after several cycles of ion sputtering and e<sup>-</sup> bombardments, shows clearly that the SEY variation is closely related to the oxidation state of the Al sample, reaching a  $\delta_{\max}$  value as low as 1.3 for our cleanest surface.

*D. R. Grosso et al in preparation*

## *XPS and SEY studies on Al: conclusion*



- Also in the case of Al the SEY decreases upon electron scrubbing.
- **The SEY measurements may be influenced by the base vacuum at which they are performed**
- Presumably little role of C and dominant role of Oxidation state to determine SEY
- **The extreme reactivity of Al surface, makes Al chambers not suitable for their e-cloud related performances unless coated with a more stable compound.**

*D. R. Grosso et al in preparation*

*TiN*

*Of interest for SuperB, Super KEKB,  
ILC Damping Rings, etc.*


## *TiN (done by S. Bini & the LNF Vacuum Group).*



*Nanocrystalline TiN thin films has been deposited on aluminum substrates by RF-magnetron sputtering. The “good” quality of the film in terms of microstructural morphology and texture was characterized by SEM and FE SEM and by X – Ray Diffraction.*

\*D.R. Grosso et al. in preparation


*On such TiN we measured SEY vs. electron Dose and...*




*TiN (at least “our”) needs scrubbing: then it reaches  $\delta_{max} \sim 1$ , which is the value quoted at KEK*

*D. R. Grosso  
et al  
in preparation*

We measured  $\delta_{max}$  vs.  $e^-$  Dose and Ion sputtering and..




*We measured XPS vs.  $e^-$  Dose and Ion sputtering and..*





*Also in TiN the SEY reduction is accompanied by C-sp<sup>2</sup> formation*



*a little (but useful) detour  
on the scrubbing process*

*Most of the data on “scrubbing” have been obtained in laboratory experiments by bombarding surfaces with 500 eV electrons for increasing Time (i.e: dose)*


$$\text{Dose} = N^{\circ} e^{-} \times t(s) \times A \text{ (mm}^2\text{)}$$

- *What energy do the  $e^{-}$  participating in the cloud have in the accelerator?*

*Simulation by F.*


*Zimmermann (2001) shows that the main contribution lies at low energy!*

- *do 10  $e^{-}$  @ 500 eV scrub as*
  - *10  $e^{-}$  @ 10 eV?*






# Scrubbing vs impinging electron energy

Comisso et al in preparation



SEY measurements for 200 eV, 50 eV and 10 eV impinging electron energy at normal incidence






$\delta_{\max}$  versus dose for different impinging electron energies at normal incidence.


*Commisso et al  
in preparation*

*We demonstrate that the potentiality of an electron beam to reduce the SEY does not only depend on its dose, but also on its energy.*

*We repeated the experiment to confirm it and to do XPS.*




*We repeated the experiment to confirm it and to do XPS.*



*Theo DEMMA performed some preliminary simulation to see if one can optimize the “scrubbing” process @ LHC*

Table 1: Parameters used for ECLLOUD simulations.


parameter	units	value
beam particle energy	$GeV$	7000
bunch spacing $t_b$	$ns$	25; 50; 75
bunch length	$m$	0.075
number of trains $N_t$	-	4
number of bunches per train $N_b$	-	72; 36; 24
bunch gap $N_g$	-	8
no. of particles per bunch	$10^{10}$	10; 3.0
length of chamber section	$m$	1
chamber radius	$m$	0.02
circumference	$m$	27000
primary photo-emission yield	-	$7.98 \cdot 10^{-4}$
maximum $SEY$ $\delta_{max}$	-	1.2(0.2)2.0
energy for max. $SEY$ $E_{max}$	eV	237






- Potential consequences of these measurements on the commissioning of LHC: calculation of the  $e^-$  dose hitting the walls versus beam parameter and energy (preliminary).

@ 50ns,  $\delta_{max} = 1.4$  equal  $e^-$  density




Log Scale!



*T. Demma et al. in preparation.*

- *Potential consequences on the commissioning of LHC: optimizing beam parameters to increase  $e^- > 30$  eV. Could be important to determine optimal n. of bunchs and bunch pattern for DR.*



*M.Commisso, R. Cimino, T. Demma, V. Baglin in preparation.*

## *What did we learn so far?*

*Al, is very reactive, ageing etc. produce Oxides with very high SEY! (If used should be coated)*

*From Surface Analysis we learn that when C on the surface forms an  $sp^2$  layer, then scrubbing is efficient and the  $\delta_{max}$  goes below 1.2!!*


*Graphitization is an essential (and quite general, but Al) ingredient in SEY reduction!*

*Is there an alternative way to graphitize samples in order to have low SEY surfaces?  
Can we deposit stable carbon or graphite coatings ?*


*CERN uses magneto-sputtering technique to grow a thick  
(0.2-10  $\mu\text{m}$ ) of a-C film on accelerator wall surfaces.*

*Results are promising and under study in terms of stability versus  
time, adhesion etc.*

*Our line of work is concentrated on creating very thin (some layers)  
“graphene” - like coatings on metal substrates to be used in  
accelerator to mimic what is actually happening during scrubbing.*



*D. R. Grosso R. Larciprete, A. di Trolio et al in preparation*



*It confirms that the best Graphene/Graphite layer we grow the lowest the SEY is !*

*Not only we start to understand what is actually happening during SEY reduction, but also using it to develop conceptually new material and coatings.*

*Results are promising and suggest that this could be the right research direction!*

*Other accurate studies are necessary to optimize growth parameters, to test the performance of material in terms of stability vs time, adhesion, cost effectiveness etc..*  
*We need to be able to produce these material in large scale for accelerators..... A lot of work!!!*



## Acknowledgments:

### in the lab:

*M. Commisso and D. R. Grosso*

*R. Larciprete, A. di Trolio (CNR-ISC), R. Flammini (CNR-IMIP)*

### *People from the accel. division*

- T. Demma, S. Bini, D. Alesini, V. Lollo, C. Vaccarezza, M. Biagini, S. Guiducci, M. Zobov, A. Drago, P. Raimondi*

### *Last but not least : the e-cloud community*

*V. Baglin, G. Bellodi, I.R Collins, M. Furman, O. Gröbner, M. Pivi,  
A. G. Mattewson<sup>+</sup>, F. Ruggero<sup>+</sup>, S. Casalboni, G. Rumolo, W. Fischer,  
F. Zimmermann, M. Palmer, R. Wanzenberg and many others.....*



announcement & invitation

# E-CLOUD'12

La Biodola, Isola d'Elba, Italy  
From 5/6 to 9/10 June 2012




E-CLOUD workshop series started at CERN in 2002.

After 10 years and stops in Napa Valley/CA (2004), Daegu/Korea (2007), and Cornell University/NY (2010), E-CLOUD'12 returns to Europe!

Topics: SEY models, e-cloud build & e-cloud effects in accelerators, beam induced multipactoring, surface properties, mitigation measures, microwave diagnostics, ...

more info will be posted at <https://cern.ch/ecloud12>

*we hope to see you there!*



Roberto Cimino ([Roberto.Cimino@Inf.infn.it](mailto:Roberto.Cimino@Inf.infn.it))  
and Frank Zimmermann ([frank.zimmermann@cern.ch](mailto:frank.zimmermann@cern.ch))